



EASTERN POLY CO., LTD

Trang Bang Industrial Park, Trang Bang District, Tay Ninh Province, Viet Nam

DATA SHEET

PP25

Minimum Average Roll Values when tested in accordance with the ASTM methods listed below.

Properties	Standard	Unit	Value(PP25)
Mass per Area		gsm	120
Tensile Strenhth MD	ASTM D-4595	KN/M	25
Tensile Strenhth CD	ASTM D-4595	KN/M	25
Tensile Elongation (MD&CD)	ASTM D-4595	%	<25
Grab Tensile Strength warp	ASTM D-4632	N	790
Grab Tensile Strength weft	ASTM D-4632	N	780
CBR Static Puncture	ASTM D-6241	N	2800
Trapezoidal Tear warp	ASTM D-4533	N	360
Trapezoidal Tear weft	ASTM D-4533	N	345
UV Resistance(retained after 500hrs)	ASTM D-4355	%	70
Apparent Opening Size	ASTM D-4751	mm	0.070
Permittivity	ASTM D-4491	cm./sec-1	0.05

Seller makes no warranty, expressed or implied, concerning the product furnished hereunder other than at the time of delivery it shall be of the quality and specification stated herein.