



EASTERN POLY CO., LTD

Trang Bang Industrial Park, Trang Bang District, Tay Ninh Province, Viet Nam

DATA SHEET

PP50

Minimum Average Roll Values when tested in accordance with the ASTM methods listed below.

Properties	Standard	Unit	Value(PP50)
Mass per Area		gsm	240
Tensile Strenhth MD	ASTM D-4595	KN/M	50
Tensile Strenhth CD	ASTM D-4595	KN/M	50
Tensile Elongation (MD&CD)	ASTM D-4595	%	<25
Grab Tensile Strength warp	ASTM D-4632	N	2060
Grab Tensile Strength weft	ASTM D-4632	N	1960
CBR Static Puncture	ASTM D-6241	N	6330
Trapezoidal Tear warp	ASTM D-4533	N	860
Trapezoidal Tear weft	ASTM D-4533	N	690
UV Resistance(retained after 500hrs)	ASTM D-4355	%	70
Apparent Opening Size	ASTM D-4751	mm	0.070
Permittivity	ASTM D-4491	cm./sec-1	0.05

Seller makes no warranty, expressed or implied, concerning the product furnished hereunder other than at the time of delivery it shall be of the quality and specification stated herein.